TECHNICAL DATA SHEET

Queensland Gaskets

ACN 60 PLUS | CORK SHEET

Fuel | Oil | Gas and Transformer Gaskets

TECHNICAL INFORMATION

ASTM Spec D1170	*Unavailable*
ASTM Spec F104	*F225000*
Binder	*Nitrile*
Cork Granule Size (mm)	*0.5/1*
Colour	*Natural*
Density (kg/m^3)	*750-900*
Hardness, Shore A	*70-80*
Compressibility at 2.76 MPa	*20-30*
Recovery after (%)	*>80*
Tensile Strength (kPa)	*>2400*
Flexibility – Original (F5)	*No Cracks*
Flex – ASTM Oil No1 70h @ 100C (F16)	*No Cracks*
Flexibility – Oven aged 70 h @ 100C (F1)	*No Cracks*
Volume Change After Immersion	
ASTM No1 Oil, 70h @ 100C (%)	*-10 to +10*
ASTM No3 Oil, 70h @ 100C (%)	*-5 to +15*
ASTM Fuel A, 22h @ 23C (%)	*-2 to +10*

Contact us to discuss requirements and place your order 07 3277 3922

All information and data quoted has been provided by our suppliers and is based upon years of experience in the production and operation of sealing elements. This data may not be used to support any warranty claims. With its publication this latest edition supersedes all previous issues and is subject to change without further notice.