TECHNICAL DATA SHEET

Queensland Gaskets

DONIT | TESNIT® BA-R302

TESNIT® BA-R302 has superior thermal resistance coupled with excellent mechanical properties and blowout safety. TESNIT® BA-R302 is designed for the most demanding high temperature applications like those within ships' engines.



PROPERTIES



APPROPRIATE INDUSTRIES & APPLICATIONS

- STEAM SUPPLY
- AUTOMOTIVE AND ENGINE BUILDING INDUSTRY
- SHIPBUILDING
- POWER PLANT
- HIGH TEMP. APPLICATIONS

Composition	Tanged carbon steel sheet sandwiched with BA-R300.
Colour	Black
Approvals	Germanischer Lloyd

Contact us to discuss requirements and place your order 07 3277 3922

All information and data quoted has been provided by Donit Tesnit and are based upon years of experience in the production and operation of sealing elements. This data may not be used to support any warranty claims. With its publication this latest edition supersedes all previous issues and is subject to change without further notice.

TECHNICAL DATA

Typical values for a thickness of 2 mm

Density	DIN 28090-2	g/cm^3	3.7
Compressibility	ASTM F36J	%	8
Recovery	ASTM F36J	%	45
Tensile strengthx	ASTM F152	MPa	/
Stress resistance	DIN 52913		
16 h, 50 MPa, 175 °C		MPa	48
16 h, 50 MPa, 300 °C		MPa	45
Specific leak rate	DIN 3535-6	mg/(s·m)	/
Thickness increase	ASTM F146		
Oil IRM 903, 5 h, 150 °C		%	5
ASTM Fuel B, 5 h, 23 °C		%	/
Compression modulus	DIN 28090-2		
At room temperature: ε_{KSW}		%	7.1
At elevated temperature: $\varepsilon_{WSW/200\ °C}$		%	6.3
Percentage creep relaxation	DIN 28090-2		
At room temperature: ε_{KRW}		%	2.2
At elevated temperature: $\varepsilon_{WRW/200\ °C}$		%	0.5
Max. operating conditions			
Peak temperature		°C/°F	650/1202
Continuous temperature		°C/°F	600/1112
- with steam		°C/°F	/
Pressure		bar/psi	/

Queensland Gaskets

Surface finish	Surface finish is 2G. Optional graphite or PTFE finish on request.
Dimensions of standard sheets	Sheet size (mm): 500 x 1400 Thickness (mm): 1.4 | 1.6 Other dimensions and thicknesses are available on request.
Tolerances	± 5 % on length and width On thickness up to 1.0 mm ± 0.1 mm On thickness above 1.0 mm ± 10 %

Acetamide	+
Acetic acid, 10%	-
Acetic acid, 100% (Glacial)	-
Acetone	?
Acetonitrile	-
Acetylene (gas)	+
Acid chlorides	-
Acrylic acid	-
Acrylonitrile	-
Adipic acid	-
Air (gas)	+
Alcohols	+
Aldehydes	?
Alum	?
Aluminium acetate	-
Aluminium chlorate	-
Aluminium chloride	-
Aluminium sulfate	-
Amines	-
Ammonia (gas)	?
Ammonium bicarbonate	+
Ammonium chloride	-
Ammonium hydroxide	+
Amyl acetate	?
Anhydrides	-
Aniline	-
Anisole	?
Argon (gas)	+
Asphalt	+
Barium chloride	-
Benzaldehyde	-
Benzene	+
Benzoic acid	?
Bio-diesel	+
Bio-ethanol	+
Black liquor	-
Borax	+
Boric acid	-
Butadiene (gas)	+
Butane (gas)	+
Butyl alcohol (Butanol)	+
Butyric acid	-
Calcium chloride	-
Calcium hydroxide	+
Carbon dioxide (gas)	+
Carbon monoxide (gas)	+
Cellosolve	?
Chlorine (gas)	-
Chlorine (in water)	-
Chlorobenzene	?
Chloroform	-
Chloroprene	?
Chlorosilanes	-
Chromic acid	-
Citric acid	-
Copper acetate	-
Copper sulfate	-
Creosote	?
Cresols (Cresylic acid)	-
Cyclohexane	+
Cyclohexanol	+
Cyclohexanone	?
Decalin	+
Dextrin	+
Dibenzyl ether	?
Dibutyl phthalate	?
Dimethylacetamide (DMA)	?
Dimethylformamide (DMF)	?

Dioxane	-
Diphyl (Dowtherm A)	+
Esters	?
Ethane (gas)	+
Ethers	?
Ethyl acetate	?
Ethyl alcohol (Ethanol)	+
Ethyl cellulose	?
Ethyl chloride (gas)	-
Ethylene (gas)	+
Ethylene glycol	+
Formaldehyde (Formalin)	?
Formamide	?
Formic acid, 10%	-
Formic acid, 85%	-
Formic acid, 100%	-
Freon-12 (R-12)	+
Freon-134a (R-134a)	+
Freon-22 (R-22)	?
Fruit juices	-
Fuel oil	+
Gasoline	+
Gelatin	+
Glycerine (Glycerol)	+
Glycols	+
Helium (gas)	+
Heptane	+
Hydraulic oil (Glycol based)	+
Hydraulic oil (Mineral type)	+
Hydraulic oil (Phosphate ester based)	?
Hydrazine	-
Hydrocarbons	+
Hydrochloric acid, 10%	-
Hydrochloric acid, 37%	-
Hydrofluoric acid, 10%	-
Hydrofluoric acid, 48%	-
Hydrogen (gas)	+
Iron sulfate	-
Isobutane (gas)	+
Isooctane	+
Isoprene	+
Isopropyl alcohol (Isopropanol)	+
Kerosene	+
Ketones	?
Lactic acid	-
Lead acetate	-
Lead arsenate	-
Magnesium sulfate	+
Maleic acid	-
Malic acid	-
Methane (gas)	+
Methyl alcohol (Methanol)	+
Methyl chloride (gas)	?
Methylene dichloride	?
Methyl ethyl ketone (MEK)	?
N-Methyl-pyrrolidone (NMP)	?
Milk	+
Mineral oil (ASTM no.1)	+
Motor oil	+
Naphtha	+
Nitric acid, 10%	-
Nitric acid, 65%	-
Nitrobenzene	-
Nitrogen (gas)	+
Nitrous gases (NOx)	-
Octane	+
Oils (Essential)	+
Oils (Vegetable)	+

Oleic acid	-
Oleum (Sulfuric acid, fuming)	-
Oxalic acid	-
Oxygen (gas)	-
Palmitic acid	-
Paraffin oil	+
Pentane	+
Perchloroethylene	-
Petroleum (Crude oil)	+
Phenol (Carbolic acid)	-
Phosphoric acid, 40%	-
Phosphoric acid, 85%	-
Phthalic acid	-
Potassium acetate	-
Potassium bicarbonate	+
Potassium carbonate	+
Potassium chloride	-
Potassium cyanide	-
Potassium dichromate	-
Potassium hydroxide	?
Potassium iodide	-
Potassium nitrate	-
Potassium permanganate	-
Propane (gas)	+
Propylene (gas)	+
Pyridine	-
Salicylic acid	-
Seawater/brine	-
Silicones (oil/grease)	+
Soaps	+
Sodium aluminate	+
Sodium bicarbonate	+
Sodium bisulfite	-
Sodium carbonate	+
Sodium chloride	-
Sodium cyanide	-
Sodium hydroxide	?
Sodium hypochlorite (Bleach)	-
Sodium silicate (Water glass)	?
Sodium sulfate	+
Sodium sulfide	-
Starch	+
Steam	?
Stearic acid	-
Styrene	?
Sugars	+
Sulfur	?
Sulfur dioxide (gas)	?
Sulfuric acid, 20%	-
Sulfuric acid, 98%	-
Sulfuryl chloride	-
Tar	+
Tartaric acid	-
Tetrahydrofuran (THF)	-
Titanium tetrachloride	-
Toluene	+
2,4-Toluenediisocyanate	?
Transformer oil (Mineral type)	+
Trichloroethylene	-
Vinegar	-
Vinyl chloride (gas)	-
Vinylidene chloride	-
Water	?
White spirits	+
Xylenes	+
Xylenol	-
Zinc sulfate	-

CHEMICAL RESISTANCE CHART

The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

\+ Recommended
? Recommendation depends on operating conditions
\- Not recommended

DONIT TESNIT®, d.o.o.

Date created 01/06/2015

Contact us to discuss requirements and place your order 07 3277 3922