GYLON® Style 3545

MATERIAL PROPERTIES*:

Color:	White
Composition:	Microcellular PTFE
Fluid Services (see chemical resistance guide)**:**	Strong caustics, strong acids, chlorine, hydrocarbons, cryogenics, glass-lined equipment and low bolt load applications[2]
Temperature[1], °F (°C)	
Minimum:	-450 (-268)
Maximum:	+500 (+260)
Pressure[1], Maximum, psig (bar):	1200 (83)
P x T (max.)[1], psig x °F (bar x °C):	
1/32 and 1/16":	350,000 (12,000)
1/8"	250,000 (8,600)
Flammability:	Will Not Support Flame
Bacterial Growth:	Will Not Support
Meets Specifications:	ABS (American Bureau of Shipping), FDA (Food and Drug Administration) 21 CFR 177.1550

TYPICAL PHYSICAL PROPERTIES*:

ASTM F36	**Compressibility**, average, %:	60-70		
ASTM F36	**Recovery**, %:	15		
ASTM F38	**Creep Relaxation,** %:	15		
ASTM D149	**Dielectric Properties,** range, volts/mil.			
	Sample conditioning	1/16"		1/8"
	3 hours at 250°F	248		244
	96 hours at 100% Relative Humidity:	222		264
ASTM F586	**Design Factors**	1/16" & Under		1/8"
	"m" factor:	2.6		2.0
	"y" factor, psi (N/mm^2):	1500 (10.3)		2200 (15.2)
ROTT	**Gasket Constants:**			
	1/16"	Gb=162.1	a=0.379	$Gs=1.35x10^{-9}$
	1/8":	Gb=92.48	a=0.468	$Gs=2.50x10^{-3}$
	3/16":	Gb=628	a=0.249	$Gs=7.93x10^{-5}$

SEALING CHARACTERISTICS*

	ASTM F37B – Fuel A	DIN 3535 – Nitrogen
Gasket Load, psi (N/mm2):	1000 (7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	580 (40)
Leakage	**0.15 ml/hr.**	**<0.015 cc/min**

Notes:

* This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties

[1] Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering. Minimum temperature rating is conservative.

[2] For flat face flanges, a minimum compressive stress of 1500psi (103N/mm2)is recommended on the contacted gasket area for 150psig (10.4bar) liquid service. Consult with the flange manufacturer to confirm that adequate compressive stress is available.

12/1/2016