TECHNICAL DATA SHEET

Queensland Gaskets

MILLBOARD 750 BIO

COMPOSITION

Ceramic free millboard based on mineral fibres*

**(exonerated from classification as a carcinogen according to Note Q in EU Commission Directive 97/69/E)*

CHARACTERISTICS

colour	beige	
classification temperature	750	°C
density	0.95	
thermal conductivity at 400 °C	0,15	W/m.°K
heat treatment loss at 800 °C	13	%
tensile strength		
longitudinal fibres	35	kg/cm²
transversal fibres	30	kg/cm²
shrinkage at 750 °C (24 hours)	< 2	%
compressibility according to ASTM F 36 method K (70 kg/cm²)	13	%
recovery	35	%

Standard size : 1000 x 1000 mm

Standard thicknesses : 2, 3, 4, 5, 6, 8, 10, 12 mm (+/- 10 %)

Contact us to discuss requirements and place your order 07 3277 3922

All information and data quoted has been provided by our suppliers and is based upon years of experience in the production and operation of sealing elements. This data may not be used to support any warranty claims. With its publication this latest edition supersedes all previous issues and is subject to change without further notice.